



SOILS/AGGREGATE TECHNICIAN REVIEW

(8:00 to 4:00)

Intro

- ☐ ATTI
- ☐ Safety
- ☐ Rounding Procedure

Thursday

ARIZ 201	Sieving of Coarse and Fine Graded Soils & Aggregates
AASHTO T 11	Materials Finer than No. 200 Sieve in Mineral Aggregates by Washing
ARIZ 210	Specific Gravity and Absorption of Coarse Aggregate
AASHTO T 19	Unit Weight and Voids in Aggregate
ARIZ 211	Specific Gravity and Absorption of Fine Aggregate
AASHTO T 255	Total Moisture Content of Aggregate by Drying
ARIZ 212	Percentage of Fractured Coarse Aggregate Particles
ARIZ 233	Flakiness of Aggregates
ARIZ 236	pH and Resistivity of Soils
Lunch 12:00 – 1:00	
ARIZ 225	Max. Dry Dens. And Opt. Moisture of Soils Method A Proctor
ARIZ 245	Max. Dry Dens. And Opt. Moisture of Soils Method D Proctor
AASHTO T 89	Liquid Limit of Soils
AASHTO T 90	Plastic Limit of Soils
AASHTO T 265	Lab Determination of Moisture Content of Soils
Hand Out Practice Calculations	

Friday

Check Practice Calculations	
AASHTO T 176	Plastic Fines in Graded Aggregates and Soils by Sand Equivalent Test
AASHTO T 21	Organic Impurities in fine Aggregates for Concrete
ARIZ 105	Sampling Soils and Aggregate
AASHTO R76	Reducing Field Samples of Aggregate to Testing Size
Hands On Practice	
Lunch 12:00 — 1:00	
Hands On Practice	1:00 — 4:00

ADOT Materials Testing Manual

<http://www.azdot.gov/business/engineering-and-construction/construction-and-materials/materials-manuals>



SOILS & AGG TECHNICIAN REVIEW TRAINING

Practice Calculations

PERCENT PASSING CALCULATION (ARIZ 201)

To calculate percent passing you will need a scientific calculator with at least one memory.

Always add up all the weights, never change the amount in the total box. If the calculated total is 1.0% or less from the total in the total box, adjust the number of the sieve weight with the largest amount retained, except for the passing #4.

COARSE SIEVE

- To get the Coarse sieve factor, divide 100 by the total weight of sample (the number in the total box).
- Place the factor in the memory of the calculator (MR+).
- Enter 100 in the calculator, subtract the first weight retained, times (x) the factor (memory recall) (MR), then the = key this will give you the % passing that sieve.
- Keeping that number in the calculator subtract the next weight retained, multiply it by the factor (MR) until all % passing is calculated and recorded.
- Continue this down to the #4 weight retained.
- Then do a check on the pass #4 by, multiplying the weight passing the #4 times the factor (MR).

FINE SIEVE

Always add up all the weights, never change the amount in the total box. If the calculated total is 1.0% or less from the total in the total box, adjust the number of the sieve weight with the largest amount retained except, for the passing #200.

- Subtract the "Total Dry Weight" from the "Dry Wt. of -#4 Split" weight to get the elutriation weight and record it in the box provided.
- To get the fine sieve factor, take the % passing the #4 (whole number) and divide it by the adjusted split weight.
- Place the factor in the memory of the calculator.
- Enter the % pass the #4 (whole number) in the calculator, subtract the weight retained on the #8 sieve, multiply, (x) it by the factor (MR) = to get the % passing the #8.
- Keeping that number in the calculator subtract the next weight retained (#10), multiply (x) it by the factor (MR) until all % passing is calculated and recorded.
- Continue this procedure down to the #200.
- Do a check on the pass #200 by multiplying the (weight passing the 200 sieve plus + the elutriation weight) by the factor (MR).

When all the percent pass results are recorded, you may now record the percent retained for each sieve. Start with the largest % pass and subtract the next smaller % pass from it. Continue this down to the #200 sieve (Rounded).

ARIZONA DEPARTMENT OF TRANSPORTATION

SOIL AND AGGREGATE TABULATION

USE CAPITAL LETTERS

LAB NUMBER				ORG NUMBER				MATL		TYPE		PUR-POSE	TEST LAB	SIZE	SIZE %
TEST NO.		LOT OR SUFFIX		SAMPLED BY				MO		DAY		YEAR		TIME	
														MILITARY TIME	
SAMPLED FROM															
LIFT NO. RDWY STATION															
IF MILEPOST, INPUT DECIMAL															
ORIGINAL SOURCE				PROJECT ENGINEER / SUPERVISOR				PROJECT NUMBER				TRACS NUMBER			
REMARKS															
Practice Calculations															
CONTACT PHONE NO. - () -															

ARIZ 201

- ☐ Dried to Constant Wt. ☐ Alt. 1 ☐ Alt. 2 ☐ Alt. 3
☐ Not Dried to Constant Wt. ☐ Alt. 4 ☐ Alt. 5

ARIZ 248

% OVERSIZE

+ 3"	+ 6"	COARSE FACTOR	=	100
				COARSE SIEVE TOTAL

WET SAMPLE PREWEIGHT =

WET WT. OF - # 4 =

- # 4 SPLIT WET WT. =

CUMULATIVE

% RET.

FINENESS

MODULUS

	WEIGHTS RETAINED				% RET.	% PASS	SPECS.	
3"								
2 1/2"								
2"								
1 1/2"		9	6	6				
1"	1	8	5	0				
3/4"	2	1	3	3				
1/2"	2	2	3	7				
3/8"	1	0	8	5				
1/4"		7	2	1				
# 4		8	8	5				
- # 4	1	1	7	8	5			
Total	2	1	6	2	7			

IF TOTAL SAMPLE IS WASHED:

UNWASHED WT. =

WASHED WT. =

ELUTRIATION =

DRY WT. OF - # 4 SPLIT

FINE FACTOR

% PASS # 4

= DRY WT. OF - # 4 SPLIT

5	1	1	
---	---	---	--

WEIGHTS RETAINED

% RET.

% PASS

SPECS.

	WEIGHTS RETAINED				% RET.	% PASS	SPECS.	
#8	1	2	5					
#10		6	6					
#16		3	2					
#30		3	4					
#40		2	9					
#50		2	2					
#100		2	7					
#200		5	1					
-#200			1					
Total	3	9	0					
Elutriation								

Dry Weight

= -#4 Split - Total Dry Weight

Liquid Limit (LL)	T - 89			T = AASHTO Tests
Plastic Limit (PL)	T - 90			SPECS.
Plasticity Index (PI) = LL - PL	T - 90			
Abrasion Method (A,B,C,D)	T - 96			
@ 100 Revolutions				%
@ 500 Revolutions				%
Absorption, H ₂ O	ARIZ 210			%
	ARIZ 211			
Specific Gravity, SSD	ARIZ 210			
	ARIZ 211			
Specific Gravity, OD	ARIZ 210			
	ARIZ 211			
Specific Gravity, Apparent	ARIZ 210			
	ARIZ 211			
Proctor Method				
Optimum Moisture				%
Max. Dry Density				PCF
Sand Equivalent	T - 176			
	ARIZ 242 (MAFC)			
At Least One Fractured Face	ARIZ 212			%
At Least Two Fractured Faces	ARIZ 212			%
Uncompacted Void Content	ARIZ 247			%
Moisture Content	T - 255			%
	T - 265			
Flakiness Index	ARIZ 233			%
Carbonates	ARIZ 238			%
pH	ARIZ 236 OR 237			
Resistivity (ohm-cm)	ARIZ 236			
Soluble Salts (PPM)	ARIZ 237			
Unit Weight	T - 19			PCF
Voids	T - 19			%
Organic Impurities	T - 21			
Chloride Content (PPM)	ARIZ 736			
Sulfate Content (PPM)	ARIZ 733			
Exchangeable Sodium (%)	ARIZ 729			
Exchangeable Sodium (PPM)	ARIZ 729			

A - ARIZ 225
 C - ARIZ 226
 D - ARIZ 226
 AD - ARIZ 245
 A1 - ARIZ 232
 AD1 - ARIZ 246

FINENESS MODULUS = $\frac{\text{TOTAL CUMULATIVE \% RET.}}{100}$

WHITE ☐
 YELLOW ☐
 BLUE ☐



RECEIVED DATE

TEST OPERATOR & DATE

SUPERVISOR & DATE

44-9353 R11/14

SEE BACK ALSO

Specific Gravity and Absorption of Fine Aggregate (ARIZ 211)

$$\text{Bulk Sp. Gr. (O.D. basis)} = \frac{A}{B + \frac{S - C}{(\quad) + (\quad) - (\quad)}} = \underline{\hspace{2cm}}$$

492.9
672.5
980.9
500.2

Where: A = mass of oven-dry sample in air, g.

B = mass of pycnometer filled with water, g.

C = mass of pycnometer with sample and water to calibration mark, g.

S = mass of saturated-surface-dry sample, g.

$$\text{Bulk Sp. Gr. (SSD basis)} = \frac{S}{B + \frac{S - C}{(\quad) + (\quad) - (\quad)}} = \underline{\hspace{2cm}}$$

$$\text{Apparent Sp. Gr.} = \frac{A}{B + \frac{A - C}{(\quad) + (\quad) - (\quad)}} = \underline{\hspace{2cm}}$$

$$\text{Absorption, percent} = \frac{S - A}{A} \times 100 = \underline{\hspace{2cm}} \%$$

Specific Gravity and Absorption of Coarse Aggregate (ARIZ 210)

$$\text{Bulk Sp. Gr. (O.D. basis)} = \frac{A}{B - C} \frac{(\quad)}{(\quad) - (\quad)} = \underline{\hspace{2cm}}$$

3950
4036
2486

Where: A = mass of oven-dry sample in air, g.

B = mass of saturated-surface-dry sample in air, g.

C = mass of saturated sample in water, g.

$$\text{Bulk Sp. Gr. (SSD basis)} = \frac{B}{B - C} \frac{(\quad)}{(\quad) - (\quad)} = \underline{\hspace{2cm}}$$

$$\text{Apparent Sp. Gr.} = \frac{A}{A - C} \frac{(\quad)}{(\quad) - (\quad)} = \underline{\hspace{2cm}}$$

$$\text{Absorption, percent} = \frac{B - A}{A} \times 100 = \underline{\hspace{2cm}} \%$$

Flakiness Index (ARIZ 233)							
Sieve Size	1-1/2"	1"	3/4"	1/2"	3/8"	1/4"	# 8
% Pass from Sieve Analysis							
% Ret. From Sieve Analysis (F)							
Weight of Test Sample			1515	1015			55
Weight Passing Slot			285	175			9
* Percent Passing Slot (P)							
NOTE: Only the size fractions which have 10 or more percent retained are tested for passing the appropriate slot, and used to determine the Flakiness Index by the equation below.				* Percent Passing Slot (P) = $\frac{\text{Weight Passing Slot}}{\text{Weight of Test Sample}} \times 100$			

$$\text{FLAKINESS INDEX} = \frac{\{F (1\frac{1}{2}'') \times P (1\frac{1}{2}'')\} + \dots + \dots + \{F (No. 8 \times P (No. 8)\}}{\{F (1-1/2'') + \dots + \dots + \{F (No. 8)\}}$$

$$\text{FLAKINESS INDEX} = \frac{\left(\frac{\text{Weight of test sample (Wt)}}{\text{Weight of fract. Particles (Wf)}} \right) + \left(\frac{\text{Weight of test sample (Wt)}}{\text{Weight of fract. Particles (W2)}} \right) + \dots}{\left(\frac{\text{Weight of test sample (Wt)}}{\text{Weight of fract. Particles (Wf)}} \right) + \left(\frac{\text{Weight of test sample (Wt)}}{\text{Weight of fract. Particles (W2)}} \right) + \dots} \times 100 = \dots \%$$

Fractured Particles (ARIZ 212)	
At least one Fractured Face:	
Wt. of test sample (Wa)	= 496
Wt. of fract. Particles(Wf)	= 444
Fract. Particles (FF) = $\frac{Wf}{Wa} \times 100$	= $\frac{444}{496} \times 100 = \dots \%$
At least two Fractured Face:	
Wt. of test sample (Wa)	= NA
Wt. of fract. Particles(W2)	= NA
Fract. Particles (FF2) = $\frac{W2}{Wa} \times 100$	= $\frac{NA}{NA} \times 100 = \dots \%$

$$\text{Moisture Content (T255, T265)} = \frac{\text{Wet Weight-Dry Weight}}{\text{Dry Weight}} \times 100 = \frac{\left(\frac{1058.9}{1035.2} \right) - \left(\frac{1035.2}{1035.2} \right) \times 100 = \dots \%$$

(ARIZ 242 FOR M.A.F.C.)

Sand Equiv.

Sand Equiv.

Sand Equiv.

Average Sand Equiv. =

Soils Practice Calculations # 4

$$PI = (LL - PL) = (\quad) - (\quad) = \quad$$



ARIZONA DEPARTMENT OF TRANSPORTATION

CALIBRATION OF PROCTOR MOLD
ARIZ 225 Appendix A

☒ Four Inch Mold ☐ Six Inch Mold Mold I. D. #: 2A

Calibration Date: _____ Calibration Expiration Date: _____

Temperature of water used for Calibration: 78 ° F

Unit Weight of Water: _____ lb. /cu. ft.

Test Operator: _____ Supervisor and Date: _____

Weight of Baseplate, Empty Mold, and Glass Plate (grams)	Weight of Baseplate, Mold Filled with Water, and Glass Plate (grams)	Weight of Water to Fill Mold (grams)
4525.6	5465.2	

$$V = \left[\begin{array}{c} \text{Volume of} \\ \text{Mold} \\ \text{(cu. ft.)} \end{array} \right] = \left[\begin{array}{c} \text{Unit Weight} \\ \text{of Water} \\ \text{(lb. / cu. ft.)} \end{array} \right] \times \left[\begin{array}{c} \text{Weight of Water to Fill Mold (grams)} \\ 453.6 \text{ (grams / lb.)} \end{array} \right]$$

$$V = \frac{(\quad)}{(\quad) \times (453.6)} = \quad \text{cu. ft.}$$

REMARKS: Practice Calculation # 4

Unit Weight of Water Table

Temp °F	lbs/cu. Ft.	Temp °F	lbs/cu. Ft.
68	62.315	77	62.243
69	62.308	78	62.234
70	62.301	79	62.225
71	62.293	80	62.216
72	62.285	81	62.206
73	62.277	82	62.196
74	62.269	83	62.186
75	62.261	84	62.176
76	62.252	85	62.166
		86	62.155

Arizona Department of Transportation
METHOD A or ALTERNATE METHOD D PROCTOR DENSITY
 (Arizona Test Method 225 or 245)

Project No: _____ Lab No : _____ Rec'd Date: 05/04/2011
 Source and Type of Material : _____
 Proctor Method Used : **Method A** _____ or **Alternate Method D** _____
 Test Operator and Date : _____ Supervisor and Date: _____

Weight of Mold = **M2** = **2015** grams Volume of Mold = _____ cu. ft. $a = VM \times 453.6 =$ _____
 $VM =$ _____

b	M1	c	WD	ED	Moisture Determination				DD
					WW	DW	d	e	
Approx % of water Added	Wt. of Sample and Mold	Wet Wt. of Sample M1 - M2	Wet Density lb/ cu ft $\frac{c}{a}$	Est. Dry Density $\frac{WD \times 100}{b + 100}$	Wet Wt. of Moisture Sample	Dry Wt. of Moisture Sample	Wt. of Water WW - DW	Percent Moisture $\frac{d \times 100}{DW}$	Dry Density lb/cu ft $\frac{WD \times 100}{e + 100}$
6	4019				334.0	309.5			
8	4129				473.6	427.7			
10	4110				399.9	356.6			
12	4058				387.7	339.9			

METHOD A

WT = _____ WR4 = _____

PR4 = $\frac{WR4}{WT} \times 100 =$ _____

ALTERNATE METHOD D

WT = _____ WR 3/4 = _____


PR 3/4 = $\frac{WR 3/4}{WT} \times 100 =$ _____ %

Coarse Aggregate Bulk Oven Dry Specific Gravity : _____

Coarse Aggregate Absorption : _____


OPTIMUM MOISTURE CONTENT = OM = _____

MAXIMUM DRY DENSITY (lb. / cu. ft.) = MD = _____



Remarks : Study Guide Calculations

Practice Calculations 4



ARIZ 236 WORK CARD **DETERMINING pH AND MINIMUM RESISTIVITY** **OF SOILS AND AGGREGATES**

Lab Number: Practice Calculations # 4

Date: 10/27/2015

Project / TRACS #: _____

Tested By: _____

MINIMUM RESISTIVITY

Range Setting		Dial Reading	Resistance, Ohms
1,000	X	5.8	=
1,000	X	4.5	=
1,000	X	4.1	=
1,000	X	2.7	=
1,000	X	1.8	=
1,000	X	1.4	=
100	X	1.9	=
100	X	3.9	=
	X		=
	X		=
	X		=

pH

Sample Weight: 50.1 g Water Weight: _____ g

Start Time: 9:00

Stir _____

Stir _____

Stir _____

Stir _____

Stir _____

Stir _____

Stir _____

Stir _____

End Time: _____

Soil Box Factor = 6.71 pH Reading = 7.86 pH = _____

Buffers used for calibration of pH meter: _____

(Minimum Resistivity, ohm-cm) = (Resistance, ohms) x (Soil Box Factor, cm)

(_____) X (_____) = _____ ohm-cm

MINIMUM RESISTIVITY = _____ **ohm-cm**



SOILS & AGG TECHNICIAN REVIEW TRAINING

Practice Calculations

Answer Key

Practice Gradation Calculations

				COARSE FACTOR				100 / 21627 = 0.004623850	
				0.004624					
Wt. Retained		% RET.		% PASS		Wt. RET. (Memory Recall) (MR)			
3"									
2 1/2"									
2"				100		100 - 966	x	0.004624	= 95.533361
1 1/2"	966	4	96	95.53336108	- 1850	x	(MR)	=	86.979239
1"	1850	9	87	86.97923891	- 2133	x	(MR)	=	77.116567
3/4"	2133	10	77	77.11656725	- 2202	x	(MR)	=	66.934850
1/2"	2237	10	67	66.93484996	- 1085	x	(MR)	=	61.917973
3/8"	1085	5	62	61.91797290	- 721	x	(MR)	=	58.584177
1/4"	721	3	59	58.58417719	- 885	x	(MR)	=	54.492070
# 4	885	5							
- # 4	11785		54	-#4 Check =	11785 x 0.004624	=	54.492070		
Total	21627								
2202		21662		-35					

2202 21662 -35

				FINE FACTOR				54 / 511 = 0.105675147	
				0.105675					
				Wt. Retained		% RET.		% PASS	
#8	125	14	40	54 - 128	x	0.105675	=	40.473581	
#10	66	7	33	40.47358121 - 66	x	(MR)	=	33.499022	
#16	32	3	30	33.49902153 - 32	x	(MR)	=	30.117417	
#30	34	3	27	30.11741683 - 34	x	(MR)	=	26.524462	
#40	29	4	23	26.52446184 - 29	x	(MR)	=	23.459883	
#50	22	2	21	23.45988258 - 22	x	(MR)	=	21.135029	
#100	27	3	18	21.13502935 - 27	x	(MR)	=	18.281800	
#200	51	5							
- # 200	1		12.9	18.28180039 - 51	x	(MR)	=	12.892368	
Total	390								
Elutriation	121			-# 200 Check = 121 + 1 = 122	x	(MR)	=	12.892368	

128 387 3

(Elutriation + - # 200's)

ARIZONA DEPARTMENT OF TRANSPORTATION

SOIL AND AGGREGATE TABULATION

USE CAPITAL LETTERS

LAB NUMBER				ORG NUMBER				MATL		TYPE		PUR-POSE	TEST LAB	SIZE	SIZE %
TEST NO.		LOT OR SUFFIX		SAMPLED BY				MO		DAY		YEAR		TIME	
														MILITARY TIME	
SAMPLED FROM															
LIFT NO. RDWY STATION															
IF MILEPOST, INPUT DECIMAL															
ORIGINAL SOURCE				PROJECT ENGINEER / SUPERVISOR				PROJECT NUMBER				TRACS NUMBER			
REMARKS															
Practice Calculations															
CONTACT PHONE NO. - () -															

ARIZ 201

- ☐ Dried to Constant Wt. ☐ Alt. 1 ☐ Alt. 2 ☐ Alt. 3
☐ Not Dried to Constant Wt. ☐ Alt. 4 ☐ Alt. 5

% OVERSIZE

+ 3"	+ 6"	COARSE FACTOR	100
		004624	COARSE SIEVE TOTAL

WET SAMPLE PREWEIGHT =

WET WT. OF - # 4 =

- # 4 SPLIT WET WT. =

	WEIGHTS RETAINED				% RET.	% PASS	SPECS.	CUMULATIVE % RET. FINENESS MODULUS
3"								
2 1/2"								
2"								
1 1/2"		9	6	6	4	96		
1"	1	8	5	0	9	87		
3/4"	2	1	3	3	10	77		
1/2"	2	2	3	7	10	67		
3/8"	1	0	8	5	5	62		
1/4"		7	2	1	3	59		
# 4		8	8	5	5			
- # 4	1	1	7	8	5	54		
Total	2	1	6	2	7			

IF TOTAL SAMPLE IS WASHED:

UNWASHED WT. =

WASHED WT. =

ELUTRIATION =

DRY WT. OF - # 4 SPLIT

5	1	1	FINE FACTOR	105675147
			105675	DRY WT. OF - # 4 SPLIT

	WEIGHTS RETAINED				% RET.	% PASS	SPECS.
#8	1	2	5		14	40	
#10		6	6		7	33	
#16		3	2		3	30	
#30		3	4		3	27	
#40		2	9		4	23	
#50		2	2		2	21	
#100		2	7		3	18	
#200		5	1		5		
-#200			1		12.9		
Total	3	9	0				
Elutriation	1	2	1				

Dry Weight

= -#4 Split - Total Dry Weight

Liquid Limit (LL)	T - 89			T = AASHTO Tests
Plastic Limit (PL)	T - 90			SPECS.
Plasticity Index (PI) = LL - PL	T - 90			
Abrasion Method (A,B,C,D)	T - 96			
@ 100 Revolutions				%
@ 500 Revolutions				%
Absorption, H ₂ O	ARIZ 210			%
	ARIZ 211			
Specific Gravity, SSD	ARIZ 210			
	ARIZ 211			
Specific Gravity, OD	ARIZ 210			
	ARIZ 211			
Specific Gravity, Apparent	ARIZ 210			
	ARIZ 211			
Proctor Method				
Optimum Moisture				%
Max. Dry Density				PCF
Sand Equivalent	T - 176			
	ARIZ 242 (MAFC)			
At Least One Fractured Face	ARIZ 212			%
At Least Two Fractured Faces	ARIZ 212			%
Uncompacted Void Content	ARIZ 247			%
Moisture Content	T - 255			%
	T - 265			
Flakiness Index	ARIZ 233			%
Carbonates	ARIZ 238			%
pH	ARIZ 236 OR 237			
Resistivity (ohm-cm)	ARIZ 236			
Soluble Salts (PPM)	ARIZ 237			
Unit Weight	T - 19			PCF
Voids	T - 19			%
Organic Impurities	T - 21			
Chloride Content (PPM)	ARIZ 736			
Sulfate Content (PPM)	ARIZ 733			
Exchangeable Sodium (%)	ARIZ 729			
Exchangeable Sodium (PPM)	ARIZ 729			

A - ARIZ 225
 C - ARIZ 226
 D - ARIZ 226
 AD - ARIZ 245
 A1 - ARIZ 232
 AD1 - ARIZ 246

FINENESS MODULUS = $\frac{\text{TOTAL CUMULATIVE \% RET.}}{100}$

WHITE ☐
 YELLOW ☐
 BLUE ☐



RECEIVED DATE

TEST OPERATOR & DATE

SUPERVISOR & DATE

SEE BACK ALSO

Specific Gravity and Absorption of Fine Aggregate (ARIZ 211)

$$\text{Bulk Sp. Gr. (O.D. basis)} = \frac{A}{B + S - C} = \frac{(\quad 492.9 \quad)}{(\quad 672.5 \quad) + (\quad 500.2 \quad) - (\quad 980.9 \quad)} = \underline{191.8} = \frac{2.570}{2.569864}$$

Where: A = mass of oven-dry sample in air, g.
 B = mass of pycnometer filled with water, g.
 C = mass of pycnometer with sample and water to calibration mark, g.
 S = mass of saturated-surface-dry sample, g.

492.9
672.5
980.9
500.2

$$\text{Bulk Sp. Gr. (SSD basis)} = \frac{S}{B + S - C} = \frac{(\quad 500.2 \quad)}{(\quad 672.5 \quad) + (\quad 500.2 \quad) - (\quad 980.9 \quad)} = \underline{191.8} = \frac{2.608}{2.607925}$$

$$\text{Apparent Sp. Gr.} = \frac{A}{B + A - C} = \frac{(\quad 492.9 \quad)}{(\quad 672.5 \quad) + (\quad 492.9 \quad) - (\quad 980.9 \quad)} = \underline{184.5} = \frac{2.672}{2.671545}$$

$$\text{Absorption, percent} = \frac{S - A}{A} \times 100 = \frac{(\quad 500.2 \quad) - (\quad 492.9 \quad)}{(\quad 492.9 \quad)} \times 100 = \underline{1.48} \% = \frac{1.48}{1.4810306}$$

Specific Gravity and Absorption of Coarse Aggregate (ARIZ 210)

$$\text{Bulk Sp. Gr. (O.D. basis)} = \frac{A}{B - C} = \frac{(\quad 3950 \quad)}{(\quad 4036 \quad) - (\quad 2486 \quad)} = \underline{1550} = \frac{2.548}{2.548387}$$

Where: A = mass of oven-dry sample in air, g.
 B = mass of saturated-surface-dry sample in air, g.
 C = mass of saturated sample in water, g.

3950
4036
2486

$$\text{Bulk Sp. Gr. (SSD basis)} = \frac{B}{B - C} = \frac{(\quad 4036 \quad)}{(\quad 4036 \quad) - (\quad 2486 \quad)} = \underline{1550} = \frac{2.604}{2.603871}$$

$$\text{Apparent Sp. Gr.} = \frac{A}{A - C} = \frac{(\quad 3950 \quad)}{(\quad 3950 \quad) - (\quad 2486 \quad)} = \underline{1464} = \frac{2.698}{2.698087}$$

$$\text{Absorption, percent} = \frac{B - A}{A} \times 100 = \frac{(\quad 4036 \quad) - (\quad 3950 \quad)}{(\quad 3950 \quad)} \times 100 = \underline{2.18} \% = \frac{2.18}{2.1772152}$$

Flakiness Index (ARIZ 233)							
Sieve Size	1-1/2"	1"	3/4"	1/2"	3/8"	1/4"	# 8
% Pass from Sieve Analysis			77	67			40
% Ret. From Sieve Analysis (F)			10	10			14
Weight of Test Sample			1515	1015			55
Weight Passing Slot			285	175			9
* Percent Passing Slot (P)			19	17			16
NOTE: Only the size fractions which have 10 or more percent retained are tested for passing the appropriate slot, and used to determine the Flakiness Index by the equation below.				* Percent Passing Slot (P) = $\frac{\text{Weight Passing Slot}}{\text{Weight of Test Sample}} \times 100$			

$$\text{FLAKINESS INDEX} = \frac{\{F (11/2") \times P (11/2")\} + \dots + \dots + \{F (No. 8 \times P (No. 8)\}}{\{F (1-1/2") + \dots + \dots + \{F (No. 8)\}}$$

$$\text{FLAKINESS INDEX} = \frac{(10 \times 19) + (10 \times 10) + (10 \times 17) + (10 \times 14) + (10 \times 16)}{(10) + (10) + (10) + (10) + (10)} = \frac{584}{34} = 17.17647\%$$

Fractured Particles (ARIZ 212)	
At least one Fractured Face:	
Wt. of test sample (Wa)	= 496
Wt. of fract. Particles(Wf)	= 444
Fract. Particles (FF) = $\frac{Wf}{Wa} \times 100$	= 90%
At least two Fractured Face:	
Wt. of test sample (Wa)	= NA
Wt. of fract. Particles(W2)	= NA
Fract. Particles (FF2) = $\frac{W2}{Wa} \times 100$	= NA%

$$\text{Moisture Content (T255, T265)} = \frac{\text{Wet Weight-Dry Weight}}{\text{Dry Weight}} \times 100 = \frac{1035.2 - 1058.9}{2.289413} \times 100 = 2.3\%$$

Sand Equivalent AASHTO T176) (ARIZ 242 FOR M.A.F.C) Sand Reading 3.8 Clay Reading 6.1 Sand Equiv. 63 62.30	Abrasion AASHTO T96) % Abrasion = Where: A = Original Mass (5000 ± 10 grams) B = Plus # 12 Material after Abrasion 100 Rev.: x 100 = % 500 Rev.: x 100 = % Type of Abrasion	Plasticity Index (AASHTO T89 & 90) Liquid Limit (LL) : Bottle # 7 Tare Wt. of Bottle: 60.08 # Blows 25 % Moisture = (Wet Wt. With Bottle) - (Dry Wt. With Bottle) (Dry Wt. With Bottle - Tare Wt. of Bottle) x 100 = (3.0 / 12.8) X 100 = 23.49256069 = (75.85 - 72.85) 3.0 x 100 = 23 % (72.85 - 60.08) 12.77 Liquid Limit = 23 (For 25 Blows)
Sand Reading 4.1 Clay Reading 6.7 Sand Equiv. 62 61.19 Sand Reading 64 Clay Reading 63.67 Average Sand Equiv. = 64 63.67	Plastic Limit (PL) : Bottle # 21 Tare Wt. of Bottle: 55.69 (Wet Wt. With Bottle) - (Dry Wt. With Bottle) (Dry Wt. With Bottle - Tare Wt. of Bottle) x 100 = (0.96 / 6.56) X 100 = 14.63414634 = (63.21 - 62.25) 0.96 x 100 = 15 % (62.25 - 55.69) 6.56 Plastic Limit = 15 Plasticity Index (PI) : PI = (LL - PL) = (23) - (15) = 8	Soils Practice Calculations # 4 Key

ARIZONA DEPARTMENT OF TRANSPORTATION

CALIBRATION OF PROCTOR MOLD

ARIZ 225 Appendix A

☒ Four Inch Mold
 ☐ Six Inch Mold
 Mold I. D. #: 2A

Calibration Date: _____ Calibration Expiration Date: _____

Temperature of water used for Calibration: 78 ° F

Unit Weight of Water: 62.234 lb. /cu. ft.

Test Operator: _____ Supervisor and Date: _____

Weight of Baseplate, Empty Mold, and Glass Plate (grams)	Weight of Baseplate, Mold Filled with Water, and Glass Plate (grams)	Weight of Water to Fill Mold (grams)
4525.6	5465.2	939.6

$$V = \left[\begin{array}{c} \text{Volume of} \\ \text{Mold} \\ \text{(cu. ft.)} \end{array} \right] = \left[\begin{array}{c} \text{Unit Weight} \\ \text{of Water} \\ \text{(lb. / cu. ft.)} \end{array} \right] \times [453.6 \text{ (grams / lb.)}]$$

$$V = \frac{(939.6)}{(62.234) \times (453.6)} = \frac{0.0333}{0.033284516} \text{ cu. ft.}$$

REMARKS: Practice Calculation key

Unit Weight of Water Table

Temp °F	lbs/cu. Ft.	Temp °F	lbs/cu. Ft.
68	62.315	77	62.243
69	62.308	78	62.234
70	62.301	79	62.225
71	62.293	80	62.216
72	62.285	81	62.206
73	62.277	82	62.196
74	62.269	83	62.186
75	62.261	84	62.176
76	62.252	85	62.166
		86	62.155

Arizona Department of Transportation
METHOD A or ALTERNATE METHOD D PROCTOR DENSITY
 (Arizona Test Method 225 or 245)

Source and Type of Material : _____


Test Operator and Date : _____ Supervisor and Date: _____

[illegible]

MAXIMUM DRY DENSITY
(lb. / cu. ft.) = MD = 126.8

[illegible][illegible]

Practice Calculations # 4



**ARIZ 236 WORK CARD
DETERMINING pH AND MINIMUM RESISTIVITY
OF SOILS AND AGGREGATES**

Lab Number: Practice Calculations Key Date: 10/27/2015

Project / TRACS #: _____ Tested By: _____

MINIMUM RESISTIVITY			
Range Setting		Dial Reading	Resistance, Ohms
1,000	X	5.8	= 5,800
1,000	X	4.5	= 4,500
1,000	X	4.1	= 4,100
1,000	X	2.7	= 2,700
1,000	X	1.8	= 1,800
1,000	X	1.4	= 1,400
100	X	1.9	= 190
100	X	3.9	= 390
	X		=
	X		=
	X		=

pH	
Sample Weight: <u>50.1</u> g	Water Weight: <u>50.1</u> g
Start Time: <u>9:00</u>	
Stir <u>9:10</u>	
Stir <u>9:20</u>	
Stir <u>9:30</u>	
Stir <u>9:40</u>	
Stir <u>9:50</u>	
Stir <u>10:00</u>	
Stir _____	
Stir _____	
End Time: <u>10:00</u>	

Soil Box Factor = 6.71 pH Reading = 7.86 pH = 7.9

Buffers used for calibration of pH meter: 7 & 10

(Minimum Resistivity, ohm-cm) = (Resistance, ohm) x (Soil Box Factor, cm)

(190) X (6.71) = 1274.9 ohm-cm

MINIMUM RESISTIVITY = 1275 ohm-cm