

# AASHTO - PERFORMANCE EXAM CHECKLIST

Applicant: \_\_\_\_\_

Date: \_\_\_\_\_

## AASHTO R66-16 Sampling Asphalt Materials

First test	Retest
Yes/No	Yes/No

**Size of Samples**

*SEC: 4.1.1*    A minimum of 1 Quart of Asphalt Binder. \_\_\_\_\_

*SEC: 4.1.2*    A minimum of 1 Quart of Emulsions. \_\_\_\_\_

**Containers**

*SEC: 5.1.1*    Containers for asphalt materials, except emulsified asphalt shall be double friction-top cans, square cans with screw tops, or small mouth cans with screw tops. \_\_\_\_\_

*SEC: 5.1.2*    Containers for Emulsion samples shall be wide mouth plastic containers. \_\_\_\_\_

*SEC: 5.2.1*    The size of the container shall correspond to the required amount of sample. \_\_\_\_\_

**Protection and Preservation of Samples**

*SEC: 6.1*    Containers shall be new, the top and container shall fit together tightly. \_\_\_\_\_

*SEC: 6.3*    If cleaning is necessary use a clean dry cloth. No solvents. \_\_\_\_\_

*SEC: 6.5*    Transferring from one container to another shall be avoided if possible. \_\_\_\_\_

*SEC: 6.6*    Sample tags are fastened to the side of the container, and clearly marked. \_\_\_\_\_

*SEC: 6.4*    Protect emulsions from freezing. \_\_\_\_\_

**Sampling**

*SEC: 7.1.1*    Draw off and discard a minimum of 1 gal. of asphalt material prior to obtaining the sample from the sampling valve. \_\_\_\_\_

*SEC: 7.1.1*    When sampling emulsified asphalt do not sample material under pressure. \_\_\_\_\_

Examiner: \_\_\_\_\_

**SCORE:**    **PASS**    **FAIL**    **FAIL**  
 Proctor Initials: 

--	--	--