

# AASHTO - PERFORMANCE EXAM CHECKLIST

Applicant: \_\_\_\_\_

Date: \_\_\_\_\_

## AASHTO R 76-23 Reducing Samples of Aggregate to Testing Size Method A

	First Test	Retest
	Yes/No	Yes/No

**Selection of Method (Verbal)**

SEC: 5. Have examinee tell you which methods are used for each type of aggregate:

Type of Aggregate	Method of Reducing
Fine Agg > SSD (Wet)	A,B,C
Coarse Aggregate	A,B
Coarse & Fine Aggregate	A,B
Fine Agg < SSD (Dryer)	A

	_____	_____
--	-------	-------

**Method A – Mechanical Splitter**

SEC: 5.1.1 Moist fine aggregate may be split with chute openings 1 ½” or wider, to reduce the sample to not less than 5000g. Then dried & reduced to test sample size using method “A”. (Verbal)

	_____	_____
--	-------	-------

SEC: 7.1 For coarse aggregate and mixed aggregates, the minimum width of the chutes shall be about 50% larger than the largest particles in the sample.

	_____	_____
--	-------	-------

SEC: 7.1 For dry fine aggregate, in which the entire sample will pass the 3/8’ sieve. The minimum width of the chutes shall be at least 50% larger than the largest particles and a max width of ¾”.

	_____	_____
--	-------	-------

SEC: 8.1 Place the sample in the hopper or pan and uniformly distribute it from edge to edge. The rate the sample is introduced shall be such as to allow free flowing through the chutes.

	_____	_____
--	-------	-------

SEC: 8.2 Reintroduce the sample from one of the receptacles into the splitter as many times as necessary to reduce the sample to the size specified. The portion collected in the other receptacle may be reserved for reduction in size for other tests.

	_____	_____
--	-------	-------

Examiner: \_\_\_\_\_

**SCORE:    PASS    FAIL    FAIL**  
 Examiner Initials: 

--	--	--	--