

---

# ATTI - PERFORMANCE CHECKLIST

---

## AASHTO T 255-00 – Total Evaporable Moisture Content of Aggregate by Drying

### Sample Preparation

- SEC: 6.1* Sample size may be as stated in Table 1 of the test procedure.
- SEC: 6.2* Sample is protected against moisture loss prior to weighing.

### Procedure

- SEC: 7.1* Determine the mass of the sample to the nearest 0.1 percent.
- SEC: 7.2* Dry thoroughly in the container by means of the selected source of heat, exercising care to avoid loss of any particles.
- SEC: 7.2* If a source of heat other than the controlled temperature oven is used, stir the sample during drying to accelerate the operation and avoid localized overheating.
- SEC: 7.3* The sample is thoroughly dry when further heating causes, or would cause, less than 0.1 percent of additional loss in mass.
- SEC: 7.4* Determine the mass of the dried sample to the nearest 0.1 percent after it has cooled sufficiently not to damage the balance.